

Eastar™ GN119

Polyethylene Terephthalate Glycol Comonomer

Eastman Chemical Company

Message:

Eastar™ GN119 Copolyester is a low-I.V. PETG, for sale only in Asia as a high-flow formulation. This product has been GREENGUARD INDOOR AIR QUALITY CERTIFIED®. The GREENGUARD INDOOR AIR QUALITY CERTIFIED® Mark is a registered certification mark used under license through the GREENGUARD Environmental Institute (GEI). GEI is an industry-independent, non-profit organization that oversees the GREENGUARD Certification Program. The GREENGUARD Certification Program is an industry independent, third-party testing program for low-emitting products and materials for indoor environments. For more information about GEI and to obtain printable certificates for Eastman™ Copolyesters, visit www.greenguard.org. Choose Eastman Chemical Company under the Manufacturer category and click search to display a list of our products.

General Information			
Features	High Flow		
	Low Viscosity		
Uses	Cosmetics		
	Personal Care		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	107		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	48.0	MPa	
Break, 23°C	24.0	MPa	
Tensile Elongation			ASTM D638
Yield, 23°C	4.0	%	
Break, 23°C	75	%	
Flexural Modulus (23°C)	1900	MPa	ASTM D790
Flexural Strength (23°C)	66.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	46	J/m	
23°C	84	J/m	
Unnotched Izod Impact			ASTM D256
-40°C	No Break		
23°C	No Break		
Instrumented Dart Impact			ASTM D3763
-40°C, Energy at Peak Load	44.0	J	

23°C, Energy at Peak Load	35.0	J	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	68.0	°C	
1.8 MPa, Unannealed	60.0	°C	
Optical	Nominal Value	Unit	Test Method
Transmittance (Total)	91.0	%	ASTM D1003
Haze	0.40	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	71.0	°C	
Drying Time	6.0	hr	
Processing (Melt) Temp	249 to 271	°C	
Mold Temperature	16.0 to 38.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

