

Tarnamid® T- 27 CF30

Polyamide 6

Grupa Azoty S.A.

Message:

It is 30% carbon fibre reinforced polyamide 6 compound, heat stabilised, good conductive and electrostatic properties.

General Information			
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Antistatic		
	Electrically Conductive		
	Heat Stabilized		
Uses	Mining Applications		
Appearance	Black		
	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.25	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	30.0	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	255	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	19200	MPa	ISO 527-2/1
Tensile Stress (Yield)	190	MPa	ISO 527-2/5
Tensile Strain (Break)	3.6	%	ISO 527-2/5
Flexural Modulus ¹	15000	MPa	ISO 178
Flexural Stress ²	260	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.6	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	50	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	9.3	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	205	°C	ISO 75-2/A
Vicat Softening Temperature	215	°C	ISO 306/B
Melting Temperature	221	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+5	ohms	IEC 60093

Volume Resistivity	1.0E+5	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Burning Rate	+		FMVSS 302
ISO Type	PA6, MHRZ, 14-190, CF30		ISO 1874
Injection	Nominal Value	Unit	
Drying Temperature	< 80.0	°C	
Suggested Max Moisture	< 0.10	%	
Suggested Max Regrind	10	%	
Processing (Melt) Temp	240 to 260	°C	
Mold Temperature	60.0 to 80.0	°C	
Injection Pressure	80.0 to 110	MPa	
Injection Rate	Moderate		
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

