

TEKAMID™ TA210G25

Polyamide 66

Mando Advanced Materials Co., Ltd.

Message:

TA210G20 is GF25% reinforced Polyamide66.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 25% filler by weight		
Uses	Application in Automobile Field		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40 - 0.80	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.60	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	167	MPa	ASTM D638
Tensile Elongation ² (Break)	3.0	%	ASTM D638
Flexural Modulus ³	7450	MPa	ASTM D790
Flexural Strength ⁴	245	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	98	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	255	°C	ASTM D648
1.8 MPa, not annealed	250	°C	ASTM D648
Peak Melting Temperature	260	°C	ASTM D3418
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	4.0 - 5.0	hr	
Rear Temperature	260 - 270	°C	
Middle Temperature	270 - 285	°C	
Front Temperature	270 - 295	°C	
Nozzle Temperature	270 - 295	°C	
Processing (Melt) Temp	270 - 295	°C	
Mold Temperature	80.0 - 100	°C	
Injection instructions			
Injection Speed: 40 to 70%Injection Pressure - 1st: 20 to 50%Injection Pressure - 2nd: 20 to 50%Injection Pressure - Back Pressure: 0 to 20%			
NOTE			
1.	5.0 mm/min		

2.	5.0 mm/min
3.	3.0 mm/min
4.	3.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

