Manner Flexible PVC M8195

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

Message:

Recommended Applications: 80°C General Purpose Non Lead Injection Molding Compound for Appliance and Automotive Harness Components. UL Recognized Component (Yellow Card).

General Information			
Features	General Purpose		
	Low (to None) Lead Content		
Uses	Appliance Components		
	Automotive Applications		
	General Purpose		
	General i alpose		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38 to 1.42	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	92 to 98		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	13.4	MPa	ASTM D638
Tensile Elongation (Break)	250	%	ASTM D638
Flammability	Nominal Value		Test Method
Flame Rating	V-2		UL 94
Additional Information	Nominal Value	Unit	
Stock Temperature - Recommended Molding	182	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

