

EnCom GF30 PPE-PA

Polyamide + PPE

EnCom, Inc.

Message:

30% Glass Filled PPE/PA Alloy

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Uses	Automotive Applications		
	Pump Parts		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30 to 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	143	MPa	ASTM D638
Tensile Elongation (Break)	6.0	%	ASTM D638
Flexural Modulus	7930	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	249	°C	
1.8 MPa, Unannealed	237	°C	
Injection	Nominal Value	Unit	
Drying Temperature	93.3 to 107	°C	
Drying Time	2.0 to 4.0	hr	
Drying Time, Maximum	7.0	hr	
Suggested Max Moisture	5.0E-4	%	
Suggested Shot Size	40 to 75	%	
Rear Temperature	260 to 299	°C	
Middle Temperature	266 to 299	°C	
Front Temperature	271 to 299	°C	
Nozzle Temperature	277 to 299	°C	
Processing (Melt) Temp	277 to 299	°C	

Mold Temperature	65.6 to 121	°C
Back Pressure	0.172 to 0.689	MPa
Screw Speed	20 to 100	rpm
Vent Depth	0.038 to 0.076	mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

