

SUMIKASUPER® LCP E6808UHF

Liquid Crystal Polymer
Sumitomo Chemical Co., Ltd.

Message:

SUMIKASUPER LCP is a thermotropic liquid crystalline polyester, showing the highest heat resistance among engineering plastics.

General Information			
UL YellowCard	E54705-100988641	E249884-100962042	
Filler / Reinforcement	Glass Fiber		
Features	Good Chemical Resistance		
	Good Moldability		
	Good Wear Resistance		
	High Flow		
	High Rigidity		
	Low Viscosity		
	Low Warpage		
Uses	Bobbins		
	Connectors		
	Electrical/Electronic Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.72	g/cm ³	ASTM D792
Molding Shrinkage			Internal Method
Flow	0.22	%	
Across Flow	1.0	%	
Water Absorption (Saturation)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	96		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	100	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus (23°C)	9400	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	120	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (6.40 mm)	350	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	240	°C	ASTM D648
CLTE			Internal Method
Flow : 150°C	1.0E-5	cm/cm/°C	
Transverse : 150°C	6.2E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Constant			ASTM D150
1 MHz	3.80		
1.00 GHz	3.40		
Dissipation Factor			ASTM D150
1 MHz	0.033		
1.00 GHz	4.0E-3		
Arc Resistance	132	sec	ASTM D495
Comparative Tracking Index	200	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.300 mm, NC, BK)	V-0		UL 94
Oxygen Index	48	%	JIS K7201
Additional Information	Nominal Value	Unit	Test Method
Soldering Resistance	290	°C	Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	130	°C	
Drying Time	4.0 to 24	hr	
Rear Temperature	280 to 320	°C	
Middle Temperature	320 to 340	°C	
Front Temperature	340 to 360	°C	
Nozzle Temperature	340 to 360	°C	
Processing (Melt) Temp	350	°C	
Injection Pressure	80.0 to 160	MPa	
Injection Rate	Moderate-Fast		
Holding Pressure	20.0 to 40.0	MPa	
Back Pressure	1.00 to 5.00	MPa	
Screw Speed	50 to 100	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

