

CP PRYME® Polycarbonate PC100RULUV-10M Clear

Polycarbonate
Chase Plastics Services Inc.

Message:

CP PRYME® Polycarbonate PC100RULUV-10M Clear is a Polycarbonate (PC) product. It is available in North America.

Characteristics include:

Good UV Resistance

UV Stabilized

General Information			
UL YellowCard	E313980-101021870		
Additive	UV Stabilizer		
Features	Good UV Resistance		
Appearance	Clear/Transparent		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Specific Volume	0.835	cm ³ /g	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	ASTM D955
Water Absorption			ASTM D570
24 hr	0.15	%	
Equilibrium, 23°C	0.35	%	
Equilibrium, 100°C	0.58	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	70		
R-Scale	118		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	62.1	MPa	
Break	65.5	MPa	
Tensile Elongation ²			ASTM D638
Yield	7.0	%	
Break	110	%	
Flexural Modulus ³ (50.0 mm Span)	2340	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 50.0 mm Span)	93.1	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	10.0	mg	ASTM D1044

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	800	J/m	ASTM D256
Unnotched Izod Impact (23°C)	3200	J/m	ASTM D256
Gardner Impact (23°C)	169	J	ASTM D3029
Tensile Impact Strength ⁵	546	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm	138	°C	
1.8 MPa, Unannealed, 6.40 mm	132	°C	
Vicat Softening Temperature	154	°C	ASTM D1525 ⁶
CLTE - Flow (-40 to 95°C)	6.8E-5	cm/cm/°C	ASTM E831
Specific Heat	1260	J/kg/°C	ASTM C351
Thermal Conductivity	0.19	W/m/K	ASTM C177
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance (2540 μm)	88.0	%	ASTM D1003
Haze (2540 μm)	1.0	%	ASTM D1003
NOTE			
1.	Type I, 51 mm/min		
2.	Type I, 51 mm/min		
3.	1.3 mm/min		
4.	1.3 mm/min		
5.	Type S		
6.	Rate B (120°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT