

TECHNYL STAR™ S 216 V35 NATURAL

Polyamide 6
Solvay Engineering Plastics

Message:
TECHNYLSTAR polyamide, reinforced with 35% of glass fibre, for injection moulding. Characterized by a high fluidity of the melt.

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 35% filler by weight		
Features		High liquidity		
Appearance		Natural color		
Processing Method		Injection molding		
Multi-Point Data		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
Part Marking Code (ISO 11469)		>PA6-GF35		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.41	--	g/cm ³	ISO 1183/A
Water Absorption (23°C, 24 hr)	0.90	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	10700	7400	MPa	ISO 527-2/1A
Tensile Stress (Break)	195	115	MPa	ISO 527-2/1A
Tensile Strain (Break)	3.0	5.5	%	ISO 527-2/1A
Flexural Modulus	10000	6200	MPa	ISO 178
Flexural Stress	295	195	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	13	19	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	75	80	kJ/m ²	ISO 179/1eU
Notched Izod Impact	13	16	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength	75	80	kJ/m ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Melting Temperature	222	--	°C	ISO 11357-3
Flammability	Dry	Conditioned		Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	220 - 225		°C	

Middle Temperature	225 - 235	°C
Front Temperature	235 - 245	°C
Mold Temperature	80.0	°C

Injection instructions

Spiral length vs standard PA: 200%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

