

Durepol® PBT A3 G20 PRTA011 BT321 MSP

Polybutylene Terephthalate

Petropol Industry and Trade of Polymers LTDA

Message:

Polyester PBT reinforced with 20% glass fiber in black, excellent mechanical and thermal properties.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Appearance	Black		
Resin ID (ISO 1043)	>PBT GF20<		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40 to 1.0	%	ASTM D955
Water Absorption (Equilibrium)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	115	MPa	ASTM D638
Tensile Elongation (Break)	3.3	%	ASTM D638
Flexural Modulus	7490	MPa	ASTM D790
Flexural Strength	179	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	205	°C	ASTM D648
Vicat Softening Temperature	210	°C	ASTM D1525 ¹
Peak Melting Temperature	220 to 228	°C	ASTM D2117
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength	17	kV/mm	ASTM D149
Dissipation Factor (1 kHz)	2.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Glow Wire Flammability Index (3.00 mm)	750	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	6.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	240 to 260	°C	
Mold Temperature	30.0 to 130	°C	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

