

DENKA ABS SR-T-7H

Acrylonitrile Butadiene Styrene

Denka Company Limited

Message:

DENKA ABS SR-T-7H is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America.

Characteristics include:

- Flame Rated
- Chemical Resistant
- Impact Resistant

General Information			
UL YellowCard	E49895-101156002	E49895-241520	
Features	Good Chemical Resistance		
	High Impact Resistance		
UL File Number	E49895		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.05	g/cm³	ASTM D792
23°C	1.05	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	11	g/10 min	ISO 1133
Molding Shrinkage (2.00 mm)	0.40 to 0.60	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	106		ASTM D785
R-Scale	100		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	42.0	MPa	ASTM D638
--	2200	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	44.0	MPa	
Break	34.0	MPa	
Nominal Tensile Strain at Break	36	%	ISO 527-2/50
Flexural Modulus			
-- ²	2100	MPa	ASTM D790
-- ³	2100	MPa	ISO 178
Flexural Strength			
-- ⁴	65.0	MPa	ASTM D790

-- ⁵	68.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	37	kJ/m ²	ISO 179
Notched Izod Impact	360	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed ⁶	86.0	°C	ASTM D648
1.8 MPa, Unannealed	78.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	97.0	°C	ASTM D1525 ⁷
--	98.0	°C	ISO 306/B
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	180 to 200	°C	
Middle Temperature	200 to 230	°C	
Front Temperature	210 to 260	°C	
Nozzle Temperature	210 to 255	°C	
Mold Temperature	40.0 to 60.0	°C	
Back Pressure	0.490 to 0.981	MPa	
Screw Speed	80 to 120	rpm	
NOTE			
1.	5.0 mm/min		
2.	15 mm/min		
3.	2.0 mm/min		
4.	15 mm/min		
5.	2.0 mm/min		
6.	Edgewise		
7.	Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT