

Akulon® F126-C

Polyamide 6
DSM Engineering Plastics

Message:

Akulon® F126-C is a polyamide 6 (nylon 6) material. This product is available in Europe, and the processing method is: film extrusion.
Akulon® The main features of the F126-C are:
Lubrication
Medium viscosity
Akulon® The typical application fields of F126-C are: movies

General Information	
Additive	Lubricant
Features	Lubrication
	Medium viscosity
Uses	Films
Forms	Particle
Processing Method	Film extrusion
Multi-Point Data	Specific Volume vs Temperature (ISO 11403-2)
	Viscosity vs. Shear Rate (ISO 11403-2)

Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Viscosity Number	164	cm ³ /g	ISO 307
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ISO 8295
With itself-dynamic, cast film	1.2		ISO 8295
With itself-static, cast film	1.5		ISO 8295
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
Tensile Modulus ¹ (50 µm, Cast Film)	460	MPa	Internal method
Tensile Stress - MD			ISO 527-3
Yield, 50 µm, cast film	32.0	MPa	ISO 527-3
50 µm, cast film	80.0	MPa	ISO 527-3
Tensile Elongation - MD (Broken, 50 µm, cast film)	350	%	ISO 527-3
Trouser Tear Resistance - MD (50 µm, Cast Film)	32.0	N/mm	ISO 6383-1
Water Vapor Transmission Rate (23°C, 85% RH, 50 µm, cast film)	35	g/m ² /24 hr	DIS 15106-1/-3
Oxygen Transmission Rate ²			DIS 15105-1/-2
0% RH : 23°C, 50.0 µm	26	cm ³ /m ² /bar/24 hr	DIS 15105-1/-2

85% RH : 23°C, 50.0 µm	38	cm ³ /m ² /bar/24 hr	DIS 15105-1/-2
Specific Heat Capacity			
--	1550	J/kg/°C	
Average: 20 to 150°C	2250	J/kg/°C	
Puncture Resistance (50.0 µm) ³	11.5	J/cm	Internal method
RSV ⁴	2.65		Internal method
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	9.0E-5	cm/cm/°C	ISO 11359-2
Optical	Nominal Value	Unit	Test Method
Transmittance (50.0 µm, Cast Film)	83.0	%	Internal method
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (260°C)	380	Pa·s	Internal method
Additional Information	Nominal Value	Unit	Test Method

Processing parameters for cast film test specimen:

Extruder Temperature: 270°C

Die Temperature: 270°C

Chill Roll Temperature: 110°C

Extrusion	Nominal Value	Unit
Drying Temperature	75.0	°C
Drying Time	8.0 - 10	hr
Cylinder Zone 1 Temp.	220	°C
Cylinder Zone 2 Temp.	240	°C
Cylinder Zone 3 Temp.	250	°C
Adapter Temperature	260	°C
Die Temperature	250	°C

NOTE

1. 50 mm/min
2. Cast Film
3. Cast Film
4. Formic Acid, 1g/100 ml

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT