

Ixan® SGA-1

Polyvinylidene Chloride

Solvay Specialty Polymers

Message:

IXAN® SGA -1 is a self-adhesive coating used as a metallized or non-metallic coating of aluminum, steel, and plastic films. This common grade can also be used as plastic coating or coating bonding primer. The resin can be dissolved in a wide range of solvents at room temperature.

General Information		
Uses	Coating application	
Agency Ratings	EC 1907/2006 (REACH)	
	Europe No 10/2011	
Appearance	White	
Forms	Powder	
Physical	Nominal Value	Unit
Density		
Volume	500	kg/m ³
Coating	1650	kg/m ³
Appearance	White powder	
Viscosity (20°C)	60	mPa · s
Heat Sealing Threshold-0.4 N/cm ¹	115	°C
Maximum heat sealing resistance ²	0.75	N/cm
Volatiles		%
Turbidity-24 hours(20°C)	77.0	μA
Solvent-Yes	Common solvents	
Films	Nominal Value	Unit
Oxygen Transmission Rate (25°C, 85% RH, 1.0 μm)	250	cm ³ /m ² /24 hr
Water Vapor Transmission Rate (38°C, 90% RH, 1.0 μm)	150	g/m ² /24 hr
Additional Information	Nominal Value	Unit

溶液制备-干燥

IXAN® SGA-1树脂可溶于许多常用溶剂,其中,酯和酮最为常用.

-溶剂可单独或混合使用.

IXAN® SGA-1溶液呈浅黄色透明状.色泽深浅取决于所用溶剂.树脂溶解浓度为200至300g /升.溶液可以在室温下制备,但可以升温至40-50°C以减少溶化时间.

-高品质涂层需要适当的干燥,以尽可能消除溶剂,形成性能最佳的涂膜.

涂布设备应该设计成可以加工溶剂型产品.

配送及存放

IXAN® SGA-1 以柔韧型中型散装容器(IBC)或用袋包好放在托盘上.为了避免降解,建议产品在低于25°C的恒温下存放.

法规信息

IXAN® SGA-1 生产用单体符合2011年1月14日欧盟委员会条例第10 / 2011的要求.

IXAN® SGA-1 完全符合美国联邦食品,药品,化妆品法案规定,适用于食品添加剂条例.

IXAN® SGA-1生产用单体符合欧洲议会(EC)签署的1907 /

2006法规及其理事会于2006年12月18日签署的有关的化学品注册,评估,授权和限制法规(REACH).

SolVin将根据需要提供进一步认证文件.

ISO 认证:

经评估,在Tavaux生产的DIOFAN偏二氯乙烯共聚物(PVDC)的生产,内部转移及交付,设计和开发管理体系的实施,符合 ISO 9001: 2008, ISO 14001: 2004 和OHSAS18001:007的要求.

NOTE

- | | |
|----|-----------------------------|
| 1. | 20 PSI-1s -1 Heating Pliers |
| 2. | 20 PSI-1s -1 Heating Pliers |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT