

# EMLON® 66 GFR 25

Polyamide 66

EMAS Plastik San.Tic.AS.

## Message:

Polyamide 66, %25 glass fiber reinforced

| General Information                               |               |                   |             |
|---------------------------------------------------|---------------|-------------------|-------------|
| Filler / Reinforcement                            | Glass Fiber   |                   |             |
| Recycled Content                                  | Yes           |                   |             |
| Physical                                          | Nominal Value | Unit              | Test Method |
| Density                                           | 1.25 to 1.30  | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage                                 | 0.35 to 0.45  | %                 |             |
| Hardness                                          | Nominal Value | Unit              | Test Method |
| Shore Hardness (Shore D)                          | 75 to 85      |                   | ISO 868     |
| Mechanical                                        | Nominal Value | Unit              | Test Method |
| Tensile Modulus                                   | 5000 to 8000  | MPa               | ISO 527-2   |
| Tensile Stress (Yield)                            | 120 to 160    | MPa               | ISO 527-2   |
| Tensile Strain (Break)                            | > 3.0         | %                 | ISO 527-2   |
| Impact                                            | Nominal Value | Unit              | Test Method |
| Notched Izod Impact Strength                      | > 8.0         | kJ/m <sup>2</sup> | ISO 180/1A  |
| Thermal                                           | Nominal Value | Unit              | Test Method |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 250           | °C                | ISO 75-2/A  |
| Vicat Softening Temperature                       | 255           | °C                | ISO 306/B   |
| Melting Temperature (DSC)                         | 265           | °C                | ISO 3146    |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

