

Sindustris ABS LXR515HJ

Acrylonitrile Butadiene Styrene

Sincerity Australia Pty Ltd.

Message:

Sindustris ABS LXR515HJ is an Acrylonitrile Butadiene Styrene (ABS) material. It is available in Asia Pacific for injection molding.

Important attributes of Sindustris ABS LXR515HJ are:

Flame Rated

Heat Resistant

Typical applications include:

Automotive

Housings

Electrical/Electronic Applications

General Information			
Features	High Heat Resistance		
Uses	Automotive Exterior Parts		
	Automotive Interior Parts		
	Electrical Housing		
	Electrical/Electronic Applications		
	Housings		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	104		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	45.1	MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Yield, 3.20 mm	> 5.0	%	
Break, 3.20 mm	30	%	
Flexural Modulus ³ (3.20 mm)	2350	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	74.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	78	J/m	
-30°C, 6.40 mm	69	J/m	
23°C, 3.20 mm	160	J/m	
23°C, 6.40 mm	140	J/m	

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm	108	°C	
1.8 MPa, Unannealed, 6.40 mm	100	°C	
Vicat Softening Temperature	107	°C	ASTM D1525 ⁵
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.010	%	
Rear Temperature	180 to 210	°C	
Middle Temperature	210 to 230	°C	
Front Temperature	230 to 240	°C	
Nozzle Temperature	230 to 240	°C	
Processing (Melt) Temp	220 to 240	°C	
Mold Temperature	40.0 to 60.0	°C	
Back Pressure	29.4 to 58.8	MPa	
Screw Speed	50 to 100	rpm	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	15 mm/min		
4.	15 mm/min		
5.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

