Epic Epoxy S7397-01

Epoxy; Epoxide

Epic Resins

Message:

Epic S7397-01 is a two component electrical potting grade epoxy resin. S7397-01 is designed with a convenient 1 :1 by weight or volume mix ratio along with a long gel time and slow cure. S7397-01 provides a blush free surface and is UL 94 V-0 recognized. S7397-01 is a slightly thicker version of S7397 that is more stable over long periods of storage.

General Information				
Uses	Electrical/Electronic Applications			
	Electronic Insulation			
Processing Method	Encapsulating			
	Potting			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.60 to 1.64	g/cm ³	ASTM D792	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D, 25°C)	70 to 72		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Glass Transition Temperature	24.0 to 28.0	°C	ASTM E1356	
CLTE - Flow	6.5E-5 to 7.5E-5	cm/cm/°C	ASTM D696	
Electrical	Nominal Value	Unit	Test Method	
Volume Resistivity	1.0E+13 to 2.0E+13	ohms•cm	ASTM D257	
Dielectric Strength (2.79 mm)	24	kV/mm	ASTM D149	
Dielectric Constant (100 kHz)	4.00 to 4.20		ASTM D2520	
Dissipation Factor (100 kHz)	0.030 to 0.050		ASTM D150	
Thermoset	Nominal Value	Unit	Test Method	
Thermoset Components				
	Mix Ratio by Volume: 1.0			

Part A

Mix Ratio by Weight: 1.0

Mix Ratio by Volume: 1.0

Part B	Mix Ratio by Weight: 1.0	Mix Ratio by Weight: 1.0		
Pot Life ¹ (25°C)	180 to 250	min		
Thermoset Mix Viscosity (25°C)	12000 to 16000	сР	ASTM D2393	
NOTE				

200 Gram Mass

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

