NEUSoft[™] 596 Ether 60

Thermoplastic Polyurethane Elastomer

NEU Specialty Engineered Materials

Message:

NEUSoft is a translucent polyether urethane based material with good elasticity, vibration dampening, abrasion and tear resistance. This series of polyurethanes are chemically resistant to hydrolysis and suitable for overmolding on polyolefins, ABS, PC, Pebax and nylon. NEUSoft 597-60 provides a good moisture and oxygen barrier as well as UV stability.

| General Information | | | |
|--------------------------------------|---------------------------------|-------|-------------|
| Features | Excellent Elastic Recovery | | |
| | Good Chemical Resistance | | |
| | Good Flexibility | | |
| | Good Melt Strength | | |
| | Good Processability | | |
| | Soft | | |
| | | | |
| Uses | Medical/Healthcare Applications | | |
| | Overmolding | | |
| | Tubing | | |
| | | | |
| Agency Ratings | ISO 10993 Part 4 1 | | |
| | ISO 10993 Part 5 1 | | |
| | USP Class VI | | |
| | | | |
| Forms | Pellets | | |
| Processing Method | Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.03 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 10 sec) | 75 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress (100% Strain) | 3.21 | МРа | ASTM D412 |
| Tensile Strength (Break) | 24.5 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 710 | % | ASTM D412 |
| Tear Strength | 55.9 | kN/m | ASTM D624 |
| Compression Set | 35 | % | ASTM D395 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

