

Latamid 66 E21 G/15

Polyamide 66

LATI S.p.A.

Message:

Compound based on Polyamide 66 (PA 66).
Toughened. Glass fibres.

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Impact Modifier		
Features	Impact Modified		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	1.0 to 1.3	%	
Flow : 2.00 mm	0.50 to 0.80	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2/1
23°C	4800	MPa	
60°C	3400	MPa	
90°C	2500	MPa	
120°C	1900	MPa	
150°C	1700	MPa	
Tensile Stress			ISO 527-2/5
Yield, 23°C	95.0	MPa	
Yield, 60°C	70.0	MPa	
Yield, 90°C	55.0	MPa	
Yield, 120°C	45.0	MPa	
Yield, 150°C	35.0	MPa	
Break, 23°C	90.0	MPa	
Break, 60°C	65.0	MPa	
Break, 90°C	45.0	MPa	
Break, 120°C	35.0	MPa	
Break, 150°C	30.0	MPa	
Tensile Strain			ISO 527-2/5
Yield, 23°C	3.0	%	
Yield, 60°C	4.8	%	
Yield, 90°C	6.0	%	
Yield, 120°C	7.0	%	
Yield, 150°C	7.0	%	

Break, 23°C	5.0	%	
Break, 60°C	7.0	%	
Break, 90°C	9.0	%	
Break, 120°C	9.0	%	
Break, 150°C	10	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	10	kJ/m ²	
-20°C	15	kJ/m ²	
23°C	20	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	85	kJ/m ²	
-20°C	80	kJ/m ²	
23°C	75	kJ/m ²	
Notched Izod Impact			ASTM D256A
-20°C, 3.20 mm	140	J/m	
23°C, 3.20 mm	200	J/m	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	255	°C	ISO 75-2/B
1.8 MPa, Unannealed	230	°C	ISO 75-2/A
Continuous Use Temperature ²	90.0	°C	
Vicat Softening Temperature	230	°C	ISO 306/B50
CLTE - Flow (30 to 100°C)	3.0E-5	cm/cm/°C	ASTM D696
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	260 to 290	°C	
Mold Temperature	60.0 to 80.0	°C	
Injection Rate	Moderate		
NOTE			
1.	at 60 Mpa of cavity pressure		
2.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

