

PETILEN G08-21TA

Low Density Polyethylene

PETKIM Petrokimya Holding A.S.

Message:

Application: Thin shrink film, industrial heavy duty bags

General Information			
Uses	Bags		
	Film		
	Heavy-duty Bags		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.919 to 0.923	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.75 to 1.0	g/10 min	ASTM D1238
Ash Content ¹	0.1	wt%	Internal Method
Film Quality ²	T		Internal Method
Swelling Ratio ³	1.44		Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss	58		ASTM D2457
Haze	8.8	%	ASTM D1003
NOTE			
1.	ALKATHENE 509		
2.	ALKATHENE 36		
3.	ALKATHENE 7		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT