Toler PP PP3338

Polypropylene Homopolymer

Toler Chemical, Inc

Message:

PP3338 is a high flow homopolymer resin with extra-high moldability. It is designated for ram- or screw-injection machines. PP3338 resin is available in pellet form.

General Information			
Features	Good Colorability		
	Good Dimensional Stability		
	Good Moldability		
	Good Processability		
	Good Surface Finish		
	High Flow		
	Homopolymer		
Uses	Containers		
	Lids		
	Shipping Containers		
	Support Trays		
	Thin-walled Parts		
Forms	Pellets		
Processing Method	Multi Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm³	ASTM D792B
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	33 to 38	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	80 to 85		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Injection Molded)	31.0 to 32.4	MPa	ASTM D638
Tensile Elongation (Yield)	11 to 13	%	ASTM D638
Flexural Modulus - 1% Secant ¹ (Injection Molded)	1140 to 1210	MPa	ASTM D790B
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	27 to 43	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	95.0	°C	ASTM D648
NOTE			

1. 1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

