

Staramide AG8

Polyamide 66

Eurostar Engineering Plastics

Message:

Staramide AG8 is a 40 % Glass Fiber Reinforced Polyamide 66 Injection Molding Resin

General Information			
UL YellowCard	E340012-100755262		
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.46	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.10 to 0.25	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	3.0	%	
Equilibrium, 23°C, 50% RH	0.90	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	114		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12000	MPa	ISO 527-2/1
Tensile Stress (Break)	205	MPa	ISO 527-2/5
Tensile Strain (Break)	3.0	%	ISO 527-2/5
Flexural Modulus ²	11000	MPa	ISO 178
Flexural Stress	295	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ³			ISO 180/1A
-40°C	11	kJ/m ²	
-30°C	12	kJ/m ²	
-20°C	12	kJ/m ²	
23°C	13	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴			
0.45 MPa, Unannealed, 100 mm Span	260	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 100 mm Span	258	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	260	°C	ISO 306/B50
--	258	°C	ISO 306/B120
Ball Pressure Test ⁵ (125°C)	Pass		IEC 60695-10-2
CLTE			ISO 11359-2

Flow : 23 to 60°C	2.1E-5	cm/cm/°C	
Transverse : 23 to 60°C	7.3E-5	cm/cm/°C	
Thermal Conductivity	0.33	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ⁶	> 1.0E+16	ohms	IEC 60093
Volume Resistivity	> 1.0E+16	ohms·cm	IEC 60093
Electric Strength (3.20 mm, in Oil)	19	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
50 Hz	3.40		
60 Hz	3.40		
1 MHz	3.20		
Dissipation Factor			IEC 60250
50 Hz	6.8E-3		
60 Hz	6.8E-3		
1 MHz	0.015		
Comparative Tracking Index			IEC 60112
--	500	V	
Solution B	350	V	
Flammability	Nominal Value	Unit	Test Method
Burning Rate			FMVSS 302
2.00 mm	6.0	mm/min	
3.00 mm	2.0	mm/min	
Flame Rating (0.750 mm, Tested by E2P)	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	650	°C	IEC 60695-2-12
Oxygen Index	27	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	260 to 280	°C	
Middle Temperature	270 to 280	°C	
Front Temperature	270 to 290	°C	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	60.0 to 90.0	°C	
NOTE			
1.	Tensile Bar		
2.	2.0 mm/min		
3.	80*10*4		
4.	120*10*4		
5.	125°C ±2°C		
6.	ROA		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

