

LNP™ COLORCOMP™ R1000SU compound

Polyamide 66
SABIC Innovative Plastics

Message:

LNP COLORCOMP* R1000SU is an unfilled Nylon 66 resin. Added features include: Heat Stabilized, UV Stabilized.
Also known as: LNP* COLORCOMP* Compound R-1000 HS UV
Product reorder name: R1000SU

General Information			
Additive	Heat Stabilizer		
	UV Stabilizer		
Features	Heat Stabilized		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density			
--	1.23	g/cm ³	ISO 1183
--	1.22	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3400	MPa	ISO 527-2/1
Tensile Stress (Yield)	75.0	MPa	ISO 527-2
Tensile Strain (Yield)	10	%	ISO 527-2
Flexural Modulus	3200	MPa	ISO 178
Flexural Stress	11.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ¹ (23°C)	4.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ² (1.8 MPa, Unannealed, 64.0 mm Span)	75.0	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	249 to 260	°C	
Middle Temperature	254 to 266	°C	
Front Temperature	260 to 271	°C	
Processing (Melt) Temp	266 to 277	°C	
Mold Temperature	60.0 to 98.9	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			

1.	80*10*4
2.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

