

# VAMPEEK B 0024

Polyetheretherketone

Vamp Tech

Message:

PEEK unfilled, high viscosity, UL 94 V0, halogen and red phosphorus free.

General Information			
Features	Halogen Free High Viscosity Low (to None) Phosphorus Content		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.70	%	
Across Flow	1.2	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3500	MPa	ASTM D638
Tensile Strength (Yield)	80.0	MPa	ASTM D638
Tensile Elongation (Break)	> 50	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	7.5	kJ/m <sup>2</sup>	ISO 180/A
Unnotched Izod Impact Strength	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	> 300	°C	ASTM D1525 <sup>1</sup>
RTI Elec	240	°C	UL 746
RTI Imp	240	°C	UL 746
RTI Str	240	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	ASTM D257
Comparative Tracking Index	200	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Injection	Nominal Value	Unit	Test Method
Drying Temperature	120	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	390	°C	
Mold Temperature	150	°C	

NOTE

1. Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

