

Hostacom M1 U01 102942

Polypropylene Homopolymer
LyondellBasell Industries

Message:

Hostacom M1 U01 102942 is a 10% talc filled PP homopolymer, with high melt flow rate, good stiffness, good toughness and high gloss. Product is available as a customized color matched, pellet form. This grade is delivered in 102942 color version.
This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Talc filler, 10% filler by weight		
Features	Rigid, good		
	Highlight		
	Homopolymer		
	High liquidity		
	Good toughness		
	General		
Uses	General		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.970	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	20.0	cm³/10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2300	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	35.0	MPa	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.5	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	50	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	60.0	°C	ISO 75-2/A
Vicat Softening Temperature	95.0	°C	ISO 306/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

