

Hostacom X 4323/3 S63

Polypropylene Copolymer

LyondellBasell Industries

Message:

Hostacom X 4323/3 S63 is a 20% mineral filled polypropylene copolymer. Low odour, low fogging and low carbon-emission. In use for interior application.

General Information	
Filler / Reinforcement	Mineral,20% Filler by Weight
Features	Copolymer
	Low to No Fogging
	Low to No Odor
Uses	Automotive Applications
	Automotive Interior Parts

Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	8.00	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant	2000	MPa	ISO 527-2
Tensile Stress (Yield)	22.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	4.0	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	11	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	58.0	°C	ISO 75-2/A
Vicat Softening Temperature	70.0	°C	ISO 306/B50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT