

# Hanwha Total PP FB53NH

Polypropylene

HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

FB53NH is a non-halogen, flame retardant polypropylene product, developed and manufactured using a method that does not contain halogen elements such as bromine or chlorine.  
This product features superior, stable flame retardant characteristics and is also environment-friendly.

General Information			
UL YellowCard	E140331-222909	E140331-222910	
Filler / Reinforcement	Glass fiber reinforced material		
Features	Good dimensional stability		
	Low smoke		
	Rigidity, high		
	Flame retardancy		
Uses	Thin wall parts		
	Electrical/Electronic Applications		
	Electrical components		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (2.00 mm)	0.60 - 0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	96		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	47.1	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	20	%	ASTM D638
Flexural Modulus <sup>3</sup>	3140	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	155	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	V-0		UL 94
Injection	Nominal Value	Unit	

Rear Temperature	170 - 180	°C
Middle Temperature	180 - 200	°C
Front Temperature	180 - 200	°C
Nozzle Temperature	190 - 210	°C
Mold Temperature	40.0 - 70.0	°C
Injection Pressure	39.2 - 78.5	MPa
Back Pressure	0.490 - 1.96	MPa

#### Injection instructions

Injection Speed: 50 to 80 %

#### NOTE

- |    |            |
|----|------------|
| 1. | 50 mm/min  |
| 2. | 50 mm/min  |
| 3. | 5.0 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

