Hanwha Total PP HJ500

Polypropylene Homopolymer

HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

HJ500 is a homo polypropylene resin for injection molding applications. This grade is designed to be processed in conventional injection molding equipment.

General Information			
UL YellowCard	E140331-222939		
Features	Rigidity, high		
	Rigidity, high		
	Highlight		
	Homopolymer		
	Scratch resistance		
	Heat resistance, high		
Uses	Kitchen utensils		
	Electrical appliances		
	Household goods		
	Toys		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	11	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	37.3	MPa	ASTM D638
Tensile Elongation (Break)	500	%	ASTM D638
Flexural Modulus	1570	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	20	J/m	ASTM D256
23°C	29	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45	110		
MPa, Unannealed)	110	°C	ASTM D648
Vicat Softening Temperature	155	°C	ASTM D1525 ¹

Injection	Nominal Value	Unit	
Rear Temperature	170 - 200	°C	
Middle Temperature	180 - 210	°C	
Front Temperature	210 - 250	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Pressure	78.5 - 118	MPa	
Holding Pressure	58.8 - 98.1	MPa	
Injection instructions			
Cooling Time: 25 to 40 sec			
NOTE			
1.	压力1 (10N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

