

PolyFibra® PF-PEJ01

Polypropylene

FuturaMat

Message:

PF-PEJ01 is an agromaterial descending from the PolyFibra range. PF-PEJ01 is a Polypropylène and wood fibers (spruce)-based product.

General Information			
Filler / Reinforcement	Wood Fiber		
Features	Biodegradable		
	Renewable Resource Content		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.70	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	74		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3410	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	46.2	MPa	
Break	45.9	MPa	
Tensile Strain			ISO 527-2
Yield	2.9	%	
Break	3.0	%	
Flexural Modulus	4620	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	14	kJ/m ²	ISO 179

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT