

LUBMER™ L4420

High Molecular Weight Polyethylene

Mitsui Chemicals America, Inc.

Message:

LUBMER™L4420 is a high molecular weight polyethylene material, which contains a filler. This product is available in North America.

LUBMER™The main features of L4420 are:

flame retardant/rated flame

Heat resistance

Typical application areas include:

engineering/industrial accessories

Automotive Industry

General Information			
Filler / Reinforcement	Filler		
Features	Heat resistance, high		
Uses	Gear		
	Car interior parts		
	Bearing		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow: 2.00mm	1.3	%	ASTM D955
Transverse flow: 2.00mm	1.2	%	ASTM D955
Water Absorption (24 hr)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	58		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break, 23°C)	46.0	MPa	ASTM D638
Tensile Elongation ² (Break, 23°C)	7.0	%	ASTM D638
Flexural Modulus ³ (23°C, 3.00mm, 48.0mm span)	2210	MPa	ASTM D790
Flexural Strength ⁴ (yield, 23°C, 3.00mm, 48.0mm span)	43.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 2.00 mm)	180	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	88.0	°C	ASTM D648
Vicat Softening Temperature	130	°C	ASTM D1525 ⁵
CLTE - Flow	1.2E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method

Volume Resistivity	1.0E+17	ohms·cm	ASTM D257
Dielectric Strength	60	kV/mm	ASTM D149
Dielectric Constant (23°C)	2.50		ASTM D150
Dissipation Factor (1 MHz)	1.5E-4		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94

Additional Information

Kinetic Coefficient of Friction, MCI Method, Lubmer-contact material, SUS 304, surface roughness, 6S: 0.17Heat generation temp, MCI Method, Lubmer-contact material, SUS 304, surface roughness, 6S: 75°C (30 MPa m/min)Critical PV value, MCI Method, Lubmer-contact material, SUS 304, surface roughness, 6S: >= 30 MPa m/minAbrasion Loss, MCI Method, Lubmer-contact material, SUS 304, surface roughness, 6S: 200E-10 cm³/kg-mVolume Resistivity, ASTM D257: 1E17 to 1E18 ohm-cmDissipation Factor, ASTM D150, 1MHz: 1E-4 to 2E-4Spiral Flow, MCI method, 4.8mm radius: 34 cm (270°C)The values listed as Mold Shrink, Linear Flow and Trans, ASTM D955, were tested in accordance with MCI methods.

NOTE

- | | |
|----|------------------|
| 1. | Type 5, 50mm/min |
| 2. | Type 5, 50mm/min |
| 3. | 5.0 mm/min |
| 4. | 5.0 mm/min |
| 5. | 压力1 (10N) |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

