

RTP ESD C 4080

Polyphthalamide

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Carbon fiber reinforced material		
Features	Antistatic property		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.25	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	125		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	15200	MPa	ASTM D638
Tensile Strength	155	MPa	ASTM D638
Tensile Elongation (Break)	1.3	%	ASTM D638
Flexural Modulus	11000	MPa	ASTM D790
Flexural Strength	248	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (6.35 mm)	48	J/m	ASTM D256
Unnotched Izod Impact (6.35 mm)	320	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	277	°C	ASTM D648
CLTE - Flow	2.7E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+6	ohms	ASTM D257
Volume Resistivity	1.0E+3	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information			
Mold Shrinkage, Linear-Flow, ASTM D955, 0.25in.: 2mil/in.			

Injection	Nominal Value	Unit
Rear Temperature	304 - 343	°C
Middle Temperature	304 - 343	°C
Front Temperature	304 - 343	°C
Mold Temperature	135 - 163	°C
Injection Pressure	68.9 - 138	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

