

Shuang-Bang AB-1014C

Polyurethane
Shuang-Bang Industrial Corp.

Message:

Two component PU Resins
General type resin (waterproof)
Because the molecular weight of two componet resin is quite low, adding and mixing adequate crosslinker is necessary. It would increase molecular weight and make more meshed PU structure, which would enhance the strength of membrane. Applied to yarn fixation, primer coating, pore filling. The high solid content would enhance water pressure resistance, gross, and firm-feeling of textile coating. Adding promotors would enhance aging condition and reinforce adhesion.
Cloth lamination. Lamination of cloth and TPU&PVC. For direct coatings.
High water resistance, non-yellowing, hydrosis resistance, good hand-feel, good peeling strength.
PU resin for direct coating. Applied to bottoming.

General Information		
Features	Crosslinkable	
	Hydrolysis Resistant	
	Moisture Resistant	
Uses	Coating Applications	
	Laminates	
Appearance	Transparent - Slight Yellow	
Additional Information	Nominal Value	Unit
Solvents	DMF/TOL	
Uncured Properties	Nominal Value	Unit
Color	Clear/Yellow Tint	
Solids Content	44 to 46	%
Viscosity (25°C)	30 to 60	Pa · s
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	0.981 to 1.96	MPa
Tensile Strength	> 9.81	MPa
Tensile Elongation at Break	> 400	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT