

Taitalac® 6000H

Acrylonitrile Butadiene Styrene

Taita Chemical Company, Ltd.

Message:

Taitalac® 6000H is an Acrylonitrile Butadiene Styrene (ABS) material. It is available in Asia Pacific or North America for extrusion.

Important attributes of Taitalac® 6000H are:

Flame Rated

Impact Resistant

Typical applications include:

Business/Office Goods

Consumer Goods

General Information			
Features	High Impact Resistance		
Uses	Business Equipment		
	Footwear		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
200°C/5.0 kg	0.50	g/10 min	
220°C/10.0 kg	5.5	g/10 min	
Molding Shrinkage - Flow	< 0.40	%	ASTM D955
Water Absorption (24 hr)	< 0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	115		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield, 23°C, 3.18 mm	46.9	MPa	
Break, 23°C, 3.18 mm	37.2	MPa	
Tensile Elongation ² (Break, 23°C, 3.18 mm)	30	%	ASTM D638
Flexural Modulus ³ (23°C)	2480	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 23°C)	71.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
23°C, 3.18 mm	340	J/m	
23°C, 6.35 mm	310	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 12.7 mm)	88.9	°C	ASTM D648
Vicat Softening Temperature	105	°C	ASTM D1525 ⁵

RTI Elec (1.57 mm)	60.0	°C	UL 746
RTI Imp (1.57 mm)	60.0	°C	UL 746
RTI Str (1.57 mm)	60.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
High Amp Arc Ignition (HAI) (1.57 mm)	200		UL 746
High Voltage Arc Tracking Rate (HVTR) (1.57 mm)	0.00	mm/min	UL 746
Hot-wire Ignition (HWI) (1.57 mm)	18	sec	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
NOTE			
1.	5.0 mm/min		
2.	5.0 mm/min		
3.	2.8 mm/min		
4.	2.8 mm/min		
5.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

