

# POLYLAN T-17H

Acrylonitrile Butadiene Styrene  
POLYMA Kunststoff GmbH & Co. KG

Message:

POLYLAN T-17H is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Europe. Primary characteristic: flame rated.

| General Information                 |               |          |                                    |
|-------------------------------------|---------------|----------|------------------------------------|
| Physical                            | Nominal Value | Unit     | Test Method                        |
| Density                             | 1.05          | g/cm³    | ISO 1183                           |
| Melt Mass-Flow Rate (MFR)           |               |          | ASTM D1238, ISO 1133               |
| 200°C/10.0 kg                       | 17            | g/10 min |                                    |
| 200°C/5.0 kg                        | 1.6           | g/10 min |                                    |
| Hardness                            | Nominal Value | Unit     | Test Method                        |
| Rockwell Hardness (R-Scale, 23°C)   | 110           |          | ASTM D785, ISO 2039-2              |
| Mechanical                          | Nominal Value | Unit     | Test Method                        |
| Tensile Modulus (23°C)              | 2650          | MPa      | ASTM D638, ISO 527-2               |
| Tensile Strength (Yield, 23°C)      | 50.0          | MPa      | ASTM D638, ISO 527-2               |
| Flexural Strength (23°C)            | 84.0          | MPa      | ASTM D790, ISO 178                 |
| Impact                              | Nominal Value | Unit     | Test Method                        |
| Notched Izod Impact (23°C, 6.35 mm) | 200           | J/m      | ASTM D256                          |
| Thermal                             | Nominal Value | Unit     | Test Method                        |
| Deflection Temperature Under Load   |               |          |                                    |
| 1.8 MPa, Unannealed, 12.7 mm        | 89.0          | °C       | ASTM D648                          |
| 1.8 MPa, Unannealed                 | 89.0          | °C       | ISO 75-2/A                         |
| 1.8 MPa, Annealed, 12.7 mm          | 101           | °C       | ASTM D648                          |
| 1.8 MPa, Annealed                   | 101           | °C       | ISO 75-2/A                         |
| Vicat Softening Temperature         | 104           | °C       | ISO 306/A, ASTM D1525 <sup>1</sup> |
| Flammability                        | Nominal Value |          | Test Method                        |
| Flame Rating (1.59 mm)              | HB            |          | UL 94                              |
| NOTE                                |               |          |                                    |

1. Loading 1 (10 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

