

HONES® PPS HS-CT15-G

Polyphenylene Sulfide

Guangdong Shunde Hones Polymer Material Co., Ltd.

Message:

Special grade of carbon fiber reinforced

General Information			
Filler / Reinforcement	Carbon Fiber		
UL File Number	E254390		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.55	g/cm ³	Internal Method
Molding Shrinkage			Internal Method
Flow : 2.00 mm	0.15	%	
Across Flow : 2.00 mm	0.30	%	
Water Absorption (23°C, 24 hr)	0.020	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	160	MPa	Internal Method
Tensile Elongation (Break)	1.2	%	Internal Method
Flexural Modulus	9000	MPa	Internal Method
Flexural Strength	210	MPa	Internal Method
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	260	°C	Internal Method
CLTE			ISO 11359-2
Flow	1.0E-5	cm/cm/°C	
Transverse	4.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.5E+2	ohms	IEC 60093
Volume Resistivity	3.0E+2	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (310°C)	300	Pa·s	ISO 11443

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

