

Surlyn Reflection Series® SURSG201UN-10GF

Polyamide 6 Alloy

LTL Color Compounders, Inc.

Message:

A glass fiber filled alloy of DuPont™ Surlyn® resin and nylon 6, molded in color applications.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (240°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	1.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	40.7	MPa	
Break	34.5	MPa	
Tensile Elongation ²			ASTM D638
Yield	7.0	%	
Break	30	%	
Flexural Modulus ³	1380	MPa	ASTM D790
Flexural Strength ⁴	46.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C	110	J/m	
23°C	290	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	60.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	60.0 to 62.8	°C	
Drying Time	6.0 to 8.0	hr	
Drying Time, Maximum	24	hr	
Suggested Shot Size	30 to 70	%	
Rear Temperature	241	°C	
Middle Temperature	241	°C	
Front Temperature	241	°C	
Processing (Melt) Temp	232 to 257	°C	
Mold Temperature	51.7 to 57.2	°C	
Back Pressure	0.345 to 0.689	MPa	
Vent Depth	0.025 to 0.038	mm	

NOTE	
1.	51 mm/min
2.	51 mm/min
3.	51 mm/min
4.	51 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT