

SHIN-A SEB-375

Epoxy; Epoxide

SHIN-A T&C;

Message:

Isocyanate Modified Epoxy (Bromine)

Solvent: Acetone/PM

Features: Silicone Modified, High Flow

General Information	
Uses	Coating Applications
	Paint
	Printed Circuit Boards

Physical	Nominal Value	Unit
Viscosity (25°C)	0.800 to 1.50	Pa·s
Bromine Content	16.5 to 18.0	wt%
Epoxy Equivalent	320 to 370	g/eq
N.V.	74.0 to 76.0	wt%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

