

RTP 1200 S-55D

Thermoplastic Polyurethane Elastomer (Polyester)

RTP Company

Message:

RTP 1200 S-55D is a thermoplastic polyurethane elastomer (polyester)(TPU-polyester) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.

General Information			
RoHS Compliance		Contact manufacturer	
Processing Method		Injection molding	
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.90	%	ASTM D955
Moisture Content	0.020	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	58		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	172	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
50% strain	15.3	MPa	ASTM D412
100% strain	16.2	MPa	ASTM D412
300% strain	35.9	MPa	ASTM D412
Tensile Strength (Yield)	41.6	MPa	ASTM D412
Tensile Elongation (Yield)	560	%	ASTM D412
Tear Strength ¹	173	kN/m	ASTM D624
Compression Set ² (23°C, 22 hr)	25	%	ASTM D395B
Injection	Nominal Value	Unit	
Drying Temperature	107	°C	
Drying Time	6.0	hr	
Dew Point	-28.9	°C	
Processing (Melt) Temp	204 - 221	°C	
Mold Temperature	26.7 - 60.0	°C	
Injection Pressure	41.4 - 103	MPa	
Injection instructions			
Desiccant Type Dryer Required.			
NOTE			
1.	C mould		
2.	Type 2		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

