

Estane® 58237 TPU

Thermoplastic Polyurethane Elastomer (Polyether)

Lubrizol Advanced Materials, Inc.

Message:

Type: Polyether Thermoplastic Polyurethane (TPU)
Special Feature: Moisture Vapor Transmission, with Good Elasticity
Processes: Extrusion: Blown, Flat Die Cast Film

General Information			
Uses	Blown Film cast film		
RoHS Compliance	RoHS compliance		
Appearance	Translucent		
Forms	Particle		
Processing Method	Blow film Extrusion cast film		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	90		ASTM D2240

Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (1000 Cycles, 1000 g, H-18 Wheel)	40.0	mg	ASTM D3389

Films	Nominal Value	Unit	Test Method
Water Vapor Transmission	740	g/m ² /24 hr	ASTM E96
Water Vapor Transmission - Mocon ¹ (38°C)	3000	g/m ² /24 hr	ASTM D6701
Kofler Melting Temperature	135	°C	Internal method

Elastomers	Nominal Value	Unit	Test Method
Tensile Set (200% Strain)	18	%	ASTM D412
Tensile Stress			ASTM D412
100% strain, 0.762mm	6.20	MPa	ASTM D412
300% strain, 0.762mm	13.8	MPa	ASTM D412
Tensile Strength (Break, 0.762 mm)	34.5	MPa	ASTM D412
Tensile Elongation (Break, 0.762 mm)	550	%	ASTM D412
Tear Strength			
0.762 mm ²	79.4	kN/m	ASTM D624
Cracking	21	kN/m	ASTM D470

Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-24.0	°C	ASTM D3418
Melting Temperature	144	°C	DSC
Extrusion	Nominal Value	Unit	
Drying Temperature	82.0	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Cylinder Zone 1 Temp.	177	°C	
Cylinder Zone 2 Temp.	182	°C	
Cylinder Zone 3 Temp.	188	°C	
Cylinder Zone 4 Temp.	193	°C	
Adapter Temperature	199	°C	
Melt Temperature	196	°C	
Die Temperature	199	°C	
Extrusion instructions			
Screens: 20-40-80 meshDew Point: -40°C			
NOTE			
1.	90% RH		
2.	C mould		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT