

# Jiangsu Meilan XXMLF2-13W

Fluoroelastomer

Jiangsu Meilan Chemical Co., Ltd.

Message:

Fluoroelastomer (F26) (FKM)

Quality Standard: Q/321200GDH010—2010

| General Information                         |                                      |                   |
|---------------------------------------------|--------------------------------------|-------------------|
| Appearance                                  | Transparent - Slight Yellow<br>White |                   |
| Physical                                    | Nominal Value                        | Unit              |
| Specific Gravity                            | 1.80 to 1.84                         | g/cm <sup>3</sup> |
| Mooney Viscosity (ML 1+10, 121°C)           | 51 to 90                             | MU                |
| Moisture Content                            | < 0.050                              | %                 |
| Oil Resistance - 1# jet fuel oil, 200°C/24h | < 6.0                                | %                 |
| Elastomers                                  | Nominal Value                        | Unit              |
| Tensile Strength                            | > 9.00                               | MPa               |
| Tensile Elongation (Break)                  | > 160                                | %                 |
| Compression Set <sup>1</sup> (200°C, 70 hr) | < 30                                 | %                 |
| NOTE                                        |                                      |                   |

1. Bisphenol-AF vulcanization system

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

