Hanwha Total PP BJ100

Polypropylene Impact Copolymer
HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

BJ100 is a block copolymer polypropylene resin for injection molding applications. This grade is designed to be processed in conventional injection molding equipment.

| General Information | | | | | |
|---------------------------------------|-----------------------------|----------|-------------|--|--|
| UL YellowCard | E140331-222890 | | | | |
| Features | Block Copolymer | | | | |
| | Rigidity, high | | | | |
| | High molecular weight | | | | |
| | Impact resistance, high | | | | |
| | Good UV resistance | | | | |
| | Good demoulding performance | | | | |
| | | | | | |
| Uses | Lawn and Garden Equipment | | | | |
| | Wheels | | | | |
| | Electrical components | | | | |
| | Tools/Parts Box | | | | |
| | Household goods | | | | |
| | Container | | | | |
| | Outdoor application | | | | |
| | | | | | |
| Forms | Particle | | | | |
| Processing Method | Injection molding | | | | |
| Physical | Nominal Value | Unit | Test Method | | |
| Density | 0.910 | g/cm³ | ASTM D1505 | | |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | | | |
| kg) | 1.5 | g/10 min | ASTM D1238 | | |
| Hardness | Nominal Value | Unit | Test Method | | |
| Rockwell Hardness (R-Scale) | 82 | | ASTM D785 | | |
| Mechanical | Nominal Value | Unit | Test Method | | |
| Tensile Strength (Yield) | 28.4 | MPa | ASTM D638 | | |
| Tensile Elongation (Break) | 500 | % | ASTM D638 | | |
| Flexural Modulus | 1270 | MPa | ASTM D790 | | |
| Impact | Nominal Value | Unit | Test Method | | |
| Notched Izod Impact | | | ASTM D256 | | |
| -20°C | 69 | J/m | ASTM D256 | | |
| 0°C | 98 | J/m | ASTM D256 | | |
| 23°C | 150 | J/m | ASTM D256 | | |
| | | | | | |

| Thermal | Nominal Value | Unit | Test Method |
|---|---------------|------|-------------|
| Deflection Temperature Under Load (0.45 | | | |
| MPa, Unannealed) | 110 | °C | ASTM D648 |
| Optical | Nominal Value | | Test Method |
| Gloss | 75 | | ASTM D2457 |
| Injection | Nominal Value | Unit | |
| Rear Temperature | 70.0 - 200 | °C | |
| Front Temperature | 210 - 230 | °C | |
| Mold Temperature | 0.00 - 50.0 | °C | |
| Injection Pressure | 78.5 - 127 | MPa | |
| Holding Pressure | 58.8 - 98.1 | MPa | |
| Injection instructions | | | |

Cooling Time: 30 to 40 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

