

Dynaflex™ G7630-9 (Black)

Thermoplastic Elastomer

PolyOne Corporation

Message:

Dynaflex™ G7630-9 (Black) is an easy-to-process universal TPE designed for a wide range of applications, including applications that must comply with FDA standards. *Kraton® Polymer manufacturing

Do not slip when holding

It can be bonded to polypropylene by overlapping molding

Soft to the touch and similar to rubber

General Information	
Features	Workability, good
	Good processing stability
	Good liquidity
	General
Uses	overmolding
	Washer
	Seals
	Soft touch application
	Soft handle
	Sporting goods
	General
	Consumer goods application field
Agency Ratings	FDA 21 CFR 177.1210 2
RoHS Compliance	RoHS compliance
Appearance	Black
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	31	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.3 - 2.1	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	29		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹			ASTM D412
100% strain, 23°C ²	0.689	MPa	ASTM D412

300% strain, 23°C ³	1.65	MPa	ASTM D412
Tensile Strength (Break, 23°C)	3.28	MPa	ASTM D412
Tensile Elongation (Break, 23°C)	650	%	ASTM D412
Tear Strength	14.9	kN/m	ASTM D624
Compression Set (23°C, 22 hr)	13	%	ASTM D395B
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 11200 sec ⁻¹)	6.40	Pa·s	ASTM D3835
Injection	Nominal Value	Unit	
Suggested Max Regrind	20	%	
Rear Temperature	160 - 188	°C	
Middle Temperature	177 - 193	°C	
Front Temperature	188 - 210	°C	
Nozzle Temperature	188 - 216	°C	
Mold Temperature	15.6 - 37.8	°C	
Back Pressure	0.00 - 0.827	MPa	
Screw Speed	40 - 100	rpm	

Injection instructions

在使用此产品之前或之后,均须用熔体流动速率较低 (0.5 - 2.5 MFR) 的聚乙烯 (PE) 或聚丙烯 (PP) 彻底进行置换.Dynaflex™ G7630-9(黑色)可利用高达 20% 的回收料同时其性能所受影响却极小,但该回收料必须是未受到污染的.为了最大限度地减小模塑期间其性能所受的影响,熔体温度应维持得尽可能低.回收料的有效性应由用户最终确定.Dynaflex™ G7630-9(黑色)具有极好的熔体稳定性.最长停留时间可能会根据机筒尺寸有所变化.通常,如果机器闲置 8 - 10 分钟或以上,则应将机筒排空.不需要干燥注射速度:1 - 3 英寸/秒第一阶段 - 提升压力:200 - 900 psi第二阶段 - 保持压力:50% 的升压保持时间(厚部件):3 - 10 秒保持时间(薄部件):1 - 3 秒

NOTE

1. 2 hours
2. Mouth die c
3. C mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT