

Hostaform® C 9021 10/9005

Acetal (POM) Copolymer

Celanese Corporation

Message:

Hostaform® C 9021 10/9005 is a nominal 9 melt flow rate acetal copolymer which is capable of being permanently marked by a laser. Parts molded from Hostaform® C 9021 10/9005 can be laser marked with barcodes, identification numbers, designs, 2-D symbology, etc.

General Information			
Features	Laser marking		
	Medium liquidity		
RoHS Compliance		Contact manufacturer	
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	8.00	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction	1.8	%	ISO 294-4
Flow direction	2.0	%	ISO 294-4
Water Absorption (Saturation, 23°C)	0.65	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2850	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	64.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	9.0	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	25	%	ISO 527-2/1A/50
Tensile Creep Modulus			ISO 899-1
1 hr	2500	MPa	ISO 899-1
1000 hr	1300	MPa	ISO 899-1
Flexural Modulus (23°C)	2700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	5.0	kJ/m ²	ISO 179/1eA
23°C	5.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	160	kJ/m ²	ISO 179/1eU
23°C, local fracture	180	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	104	°C	ISO 75-2/A
Melting Temperature ¹	166	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2

Flow	1.1E-4	cm/cm/°C	ISO 11359-2
Lateral	1.1E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Dielectric Strength	35	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.00		IEC 60250
1 MHz	4.00		IEC 60250
Dissipation Factor			IEC 60250
100 Hz	2.0E-3		IEC 60250
1 MHz	5.0E-3		IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	HB		UL 94
3.00 mm	HB		UL 94
Fill Analysis	Nominal Value	Unit	Test Method
Density of Melt	1.200	g/cm ³	Internal method
Ejection Temperature	165	°C	Internal method
Specific Heat Capacity of Melt	2210	J/kg/°C	Internal method
Thermal Conductivity of Melt	0.16	W/m/K	Internal method
Effective Thermal Diffusivity	0.0485	cSt	Internal method
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.15	%	
Hopper Temperature	20.0 - 30.0	°C	
Rear Temperature	170 - 180	°C	
Middle Temperature	180 - 190	°C	
Front Temperature	190 - 200	°C	
Nozzle Temperature	190 - 210	°C	
Processing (Melt) Temp	190 - 210	°C	
Mold Temperature	80.0 - 120	°C	
Injection Pressure	60.0 - 120	MPa	
Injection Rate	Slow-Moderate		
Holding Pressure	60.0 - 120	MPa	
Back Pressure	0.00 - 4.00	MPa	
Injection instructions			
Manifold Temperature: 190 to 210°CZone 4 Temperature: 190 to 210°CFeed Temperature: 60 to 80°C			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

