

LG ABS MA201

Acrylonitrile Butadiene Styrene

LG Chem Ltd.

Message:

Description
General Purpose, Low Gloss
Application
Automotive Sheet, Semi-Conductor Tray

General Information			
UL YellowCard	E67171-101159484		
Features	Gloss, low		
Uses	Application in Automobile Field		
Processing Method	Extrusion		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.70	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.19	%	ASTM D570

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	51.0	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	> 30	%	ASTM D638
Flexural Modulus ³ (6.40 mm)	2550	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 6.40 mm)	73.5	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C, 3.20 mm	190	J/m	ASTM D256
-20°C, 6.40 mm	110	J/m	ASTM D256
23°C, 3.20 mm	390	J/m	ASTM D256
23°C, 6.40 mm	250	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁵ (0.45 MPa, Unannealed, 6.40 mm)	92.0	°C	ASTM D648
Vicat Softening Temperature	100	°C	ASTM D1525 ⁶

Flammability	Nominal Value	Test Method
Flame Rating		UL 94
0.800 mm	HB	UL 94

1.60 mm	HB	UL 94
2.50 mm	HB	UL 94
3.20 mm	HB	UL 94

Injection	Nominal Value	Unit
Drying Temperature	70.0 - 80.0	°C
Drying Time	3.0 - 4.0	hr
Suggested Max Moisture	< 0.010	%
Rear Temperature	180 - 200	°C
Middle Temperature	190 - 210	°C
Front Temperature	200 - 230	°C
Nozzle Temperature	200 - 230	°C
Processing (Melt) Temp	200 - 230	°C
Mold Temperature	40.0 - 60.0	°C
Back Pressure	29.4 - 58.8	MPa
Screw Speed	30 - 60	rpm

Extrusion	Nominal Value	Unit
Drying Temperature	70.0 - 80.0	°C
Drying Time	3.0 - 4.0	hr
Suggested Max Moisture	< 0.010	%
Cylinder Zone 1 Temp.	180 - 200	°C
Cylinder Zone 2 Temp.	190 - 210	°C
Cylinder Zone 3 Temp.	200 - 230	°C
Cylinder Zone 4 Temp.	200 - 230	°C
Adapter Temperature	200 - 230	°C
Melt Temperature	200 - 230	°C
Die Temperature	200 - 230	°C

Extrusion instructions

Top RollStack Temperature: 70 to 100°C Middle RollStack Temperature: 70 to 90°C Bottom RollStack Temperature: 60 to 90°C

NOTE

1. 50 mm/min
2. 50 mm/min
3. 15 mm/min
4. 15 mm/min
5. 18.6kg
6. 速率 A (50°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

