

ESTADIENE 1016 HT V0

Acrylonitrile Butadiene Styrene

Cossa Polimeri S.r.l.

Message:

ESTADIENE 1016 HT V0 is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Europe. Applications of ESTADIENE 1016 HT V0 include electrical/electronic applications, engineering/industrial parts and furniture.

Characteristics include:

- Flame Rated
- Flame Retardant
- Good Processability
- Halogen Free
- Heat Resistant

General Information			
Features	Bromine Free		
	Flame Retardant		
	Good Processability		
	High Heat Resistance		
Uses	Electrical/Electronic Applications		
	Engineering Parts		
	Furniture		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
220°C/10.0 kg	4.0	g/10 min	
240°C/5.0 kg	14	g/10 min	
Molding Shrinkage - Flow	0.30 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	50.0	MPa	
Break	43.0	MPa	
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	2700	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	70	J/m	
23°C	90	J/m	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			

--	123	°C	ASTM D1525 ¹
--	115	°C	ASTM D1525 ²
Ball Indentation Temperature	105	°C	IEC 60335-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Ignition Temperature (2.00 mm)	960	°C	IEC 60695-2-13
NOTE			
1.	Rate A (50°C/h), Loading 1 (10 N)		
2.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT