

NOVALAC RX®849

Phenolic

Vyncolit N.V.

Message:

NOVALAC RX®849 is a phenolic (Phenolic) material, and its filler is glass fiber reinforced material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing methods are: resin transfer molding, compression molding or injection molding. NOVALAC RX®The main features of the 849 are:

- chemical resistance
- high strength
- Creep resistance
- Good dimensional stability
- Good toughness
- Typical application areas include:
 - Electrical/electronic applications
 - engineering/industrial accessories
 - electrical appliances
 - House
 - Tools

General Information	
Filler / Reinforcement	Glass fiber reinforced material
Features	Ultra high toughness
	Good dimensional stability
	Low smoke
	High strength
	Antibacterial property
	Solvent resistance
	Good creep resistance
	alkali resistance
	acid resistance
Uses	Membrane key switch
	Pump parts
	Gear
	Electrical/Electronic Applications
	Electrical appliances
	Power/other tools
	Connector
	Application in Automobile Field
	Shell
Forms	Particle
Processing Method	Resin transfer molding
	Compression molding

Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.00	g/cm ³	ASTM D792, ISO 1183
Bulk Factor	3.0		ASTM D1895
Molding Shrinkage			
Flow: Molding	0.050	%	ASTM D955
Flow direction	0.050	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.020	%	ASTM D570, ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
E scale	85		ASTM D785
E scale	80		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			
Fracture	50.0	MPa	ISO 527-2
--	44.8	MPa	ASTM D638
Flexural Modulus			
--	20700	MPa	ASTM D790
--	16000	MPa	ISO 178
Flexural Strength			
--	93.1	MPa	ASTM D790
--	100	MPa	ISO 178
Compressive Strength	176	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
--	48	J/m	ASTM D256A
--	4.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, not annealed	271	°C	ASTM D648
1.8 MPa, not annealed	190	°C	ISO 75-2/A
Linear thermal expansion coefficient			ASTM D696
Flow	1.1E-5	cm/cm/°C	ASTM D696
Lateral	2.6E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.86	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength			
-- ¹	12	kV/mm	ASTM D149
-- ²	8.3	kV/mm	ASTM D149
--	12	kV/mm	IEC 60243-1
Arc Resistance	185	sec	ASTM D495

Injection	Nominal Value	Unit
Rear Temperature	60.0	°C
Middle Temperature	73.9	°C
Nozzle Temperature	87.8	°C
Processing (Melt) Temp	98.9 - 116	°C
Mold Temperature	166 - 188	°C
Back Pressure	0.207	MPa

Injection instructions

Plastication: 50rpm Injection Pressure: Set to give 3 to 5 seconds injection time Hold Pressure: 50 to 100% of injection pressure Hold Time: 10 sec minimum Cure Time, 0.125 in: 30 to 35 sec The value listed as Thermal Conductivity, ASTM C177, was tested in accordance with ASTM F433. The value listed as Molding Shrinkage, ISO 294-4, was tested in accordance with ISO 2577 using compression molded specimens. Water Absorption, ASTM D570, 48 hrs, 50°C: 0.15% Flexural Strain, ASTM D790: 0.44% DTUL @264psi - Unannealed, ASTM D648, Post Baked: 550°F Dielectric Strength, ASTM D149, 60 Hz, Method A, dry: 310 V/mil Dielectric Strength, ASTM D149, 60 Hz, Method B, dry: 210 V/mil Compressive Strength, ISO 604: 280 MPa Dielectric Strength, IEC 243, Method A, wet: 12 V/mil Compression and Transfer Molding Conditions:
Preforming Pressure: 8000 to 12000 psi
Preheat Temperature: 210 to 235 °F
Preheat Time: 45 sec
Mold Temperature: 330 to 360 °F
Compression Mold Pressure: 2500 to 5000 psi
Transfer Mold Pressure: 4000 to 6000 psi
Cure Time, 0.125 in: 40 to 50 sec

NOTE

1. Method A (short time)
2. Method B (step by step)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT