

TAROLOX 10 K6

Polybutylene Terephthalate

Taro Plast S.p.A.

Message:

TAROLOX 10 K6 is a Polybutylene Terephthalate (PBT) product filled with 30% glass bead. It can be processed by injection molding and is available in Europe.

Characteristics include:

- Flame Rated
- Good Stiffness
- Medium Viscosity
- Warp Resistant

General Information			
Filler / Reinforcement	Glass Bead,30% Filler by Weight		
Features	Good Flow		
	Good Stiffness		
	Low Warpage		
	Medium Viscosity		
Appearance	Colors Available		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.55	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	15	g/10 min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.40 to 0.70	%	
Flow	0.30 to 0.60	%	
Water Absorption			ISO 62
23°C, 24 hr	0.050	%	
Saturation, 23°C	0.24	%	
Granule Humidity ¹	< 0.050	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6500	MPa	ISO 527-2/1
Tensile Stress (Break)	110	MPa	ISO 527-2/50
Tensile Strain (Break)	2.5	%	ISO 527-2/50
Flexural Modulus ²	6000	MPa	ISO 178
Flexural Stress ³	130	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C)	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature ⁴			
0.45 MPa, Unannealed	190	°C	ISO 75-2/B
1.8 MPa, Unannealed	145	°C	ISO 75-2/A
Vicat Softening Temperature	205	°C	ISO 306/B50
Ball Pressure Test (205°C)	Pass		IEC 60695-10-2
Melting Temperature	225	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	400	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	650	°C	IEC 60695-2-12
Oxygen Index	20	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature			
--	100	°C	
Pre-heater	120 to 130	°C	
Drying Time			
--	1.0 to 2.0	hr	
Pre-heater	3.0	hr	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	80.0 to 110	°C	
Injection Rate	Moderate-Fast		
NOTE			
1.	TARO 002		
2.	1.0 mm/min		
3.	1.0 mm/min		
4.	120°C/hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

