Daelim Po1y® XP3200

Metallocene Linear Low Density Polyethylene DAELIM INDUSTRIAL CO., LTD.

Message:

Daelim Po1y®XP3200 is a metallocene linear low density polyethylene product. It is available in Europe or Asia Pacific. Daelim Po1y®XP3200 applications include bags/linings, movies, agriculture, food contact applications and coating applications.

Features include:

Antiblock software

high gloss

slide

processing aids

Antioxidants

General Information				
Additive	Processing aid			
	Anti-caking agent			
	Antioxidation			
	slip agent			
Features	Rigid, good			
	Highlight			
	smoothness			
	Anti-caking property			
	Antioxidation			
	Definition, high			
	Good toughness			
Uses	Films			
	Laminate			
	Agricultural application			
	Heavy packing bag			
Agency Ratings	FDA 21 CFR 177.1520			
Physical	Nominal Value	Unit	Test Method	
Density	0.921	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (MFR) (190°C/2.16	1.2	(10 i	ACTNA D1220	
kg)	1.2	g/10 min	ASTM D1238	
Films	Nominal Value	Unit	Test Method	
Tensile Strength	50.0	MD	ASTM D882	
MD: Broken, 30 μm, blown film	59.8	MPa	ASTM D882	
TD: Broken, 30 µm, blown film	48.1	MPa	ASTM D882	
Tensile Elongation		2/	ASTM D882	
MD: Broken, 30 µm, blown film	550	%	ASTM D882	

TD: Broken, 30 µm, blown film	590	%	ASTM D882
Dart Drop Impact (30 µm, Blown Film)	150	g	ASTM D1709A
Elastomers	Nominal Value	Unit	Test Method
Tear Strength			ASTM D1004
Lateral flow: 0.0300mm	127	kN/m	ASTM D1004
Traffic: 0.0300mm	125	kN/m	ASTM D1004
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	107	°C	ASTM D1525
Peak Melting Temperature	115	°C	ASTM D3418
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 30.0 μm, Blown Film)	89		ASTM D2457
Haze (30.0 μm, Blown Film)	18	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	150 - 200	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

