Sumikon® FM-MK-150

Polyphenylene Sulfide

SBHPP

Message:

SUMIKON® FM-MK-150 is Glass fiber and inorganic filler filled Polyphenylene sulfide resin molding compound with good mechanical property grade. This grade is official registered UL with V-0 (t=1.0).

| General Information | | | |
|---|---------------------------------|-------|-----------------|
| Filler / Reinforcement | Glass fiber reinforced material | | |
| | Inorganic filler | | |
| | | | |
| RoHS Compliance | RoHS compliance | | |
| Appearance | Black | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 2.00 | g/cm³ | ASTM D792 |
| Molding Shrinkage | | | Internal method |
| Flow | 0.20 | % | Internal method |
| Transverse flow | 0.30 | % | Internal method |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 76.0 | MPa | ASTM D638 |
| Flexural Modulus | 17000 | MPa | ASTM D790 |
| Flexural Strength | 146 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 42 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | > 260 | °C | ASTM D648 |
| Coefficient of Linear Thermal Expansion | | | TMA |
| MD | 17 | ppm | TMA |
| TD | 23 | ppm | TMA |
| Flammability | Nominal Value | | Test Method |
| Flame Rating (1.0 mm) | V-0 | | UL 94 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

