

GLAMIDE® T-662

Polyamide 66

TOYOBO America, Inc.

Message:

GLAMIDE®T-662 is a polyamide 66 (nylon 66) product. It is available in North America. The main characteristics are: flame retardant/rated flame.

General Information				
Forms		Particle		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.14	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow				ASTM D955
1.00 mm	0.60 - 1.2	--	%	ASTM D955
3.00 mm	1.5 - 2.2	--	%	ASTM D955
Water Absorption				ASTM D570
24 hr	1.2	--	%	ASTM D570
Equilibrium, 65% RH	2.5	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	120	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength				ASTM D638
Yield, -40°C	116	110	MPa	ASTM D638
Yield, 23°C	82.0	50.0	MPa	ASTM D638
Yield, 80°C	38.0	28.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	120	200	%	ASTM D638
Flexural Modulus				ASTM D790
-40°C	4300	4000	MPa	ASTM D790
23°C	2900	1400	MPa	ASTM D790
80°C	1000	600	MPa	ASTM D790
Flexural Strength				ASTM D790
Yield, -40°C	140	120	MPa	ASTM D790
Yield, 23°C	117	66.0	MPa	ASTM D790
Yield, 80°C	66.0	40.0	MPa	ASTM D790
Compressive Strength (23°C)	90.0	--	MPa	ASTM D695
Taber Abrasion Resistance (1000 Cycles, CS-17 Wheel)	8.00	--	mg	ASTM D1044
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact				ASTM D256
-40°C	35	40	J/m	ASTM D256

23°C	45	300	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, not annealed	230	--	°C	ASTM D648
1.8 MPa, not annealed	80.0	--	°C	ASTM D648
CLTE - Flow	8.0E-5	--	cm/cm/°C	ASTM D696
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	ASTM D257
Dielectric Strength (2.00 mm)	20	13	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	3.90	6.50		ASTM D150
Arc Resistance	120	110	sec	ASTM D495
Comparative Tracking Index	600	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	HB	--		UL 94

Additional Information

干燥

Comparative Tracking Index, IEC Method: >600 V

调节后的

Tensile Elongation, ASTM D638, 23°C: >200 %Volume Resistivity, ASTM D257: 1e10 to 1e11 ohm-mComparative Tracking Index, IEC Method: >600 V

Injection	Dry	Unit
Processing (Melt) Temp	270 - 290	°C
Mold Temperature	40.0 - 80.0	°C
Injection Pressure	30.0 - 40.0	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT