# TechnoElast 9075

## Styrene Ethylene Butylene Styrene Block Copolymer

## TechnoCompound GmbH

#### Message:

The TechnoElast TPE compounds are a new, innovative product range of TechnoCompound based on styrene block copolymers. TechnoElast TPE compounds with adjustable melt flow rates possess good insulation properties, good workability, offer good thermal stability, outstanding absorption characteristics as well as elastic memory.

General Information				
Features	Block Copolymer			
	Resilient recovery, excellent			
	Good liquidity			
	Thermal stability, good			
Uses	Membrane key switch			
	Electrical/Electronic Applications			
	Electrical housing			
	Insulating material			
	Seals			
	Parts under the hood of a car			
	Application in Automobile Field			
	Car interior parts			
	Automotive exterior parts			
	Shell			
Forms	Particle			
Processing Method	Injection molding			
Physical	Nominal Value	Unit	Test Method	
Density	1.15	g/cm³	ISO 1183	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	75		ISO 868	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Stress (Break)	8.00	MPa	ISO 527-2	
Tensile Strain (Break)	250	%	ISO 527-2	
Additional Information				

tested in accordance with DIN 53504. The value listed as Tensile Strain at Break, ISO 527-1, -2, was tested in accordance with DIN 53504. Moisture Content, Infared 105°C, 15 min: 250%

Injection	Nominal Value	Unit
Drying Temperature	60.0 - 80.0	°C
Drying Time	2.0	hr

Processing (Melt) Temp	180 - 220	°C
Mold Temperature	20.0 - 40.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

