

Durethan® BC 30 S 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, non-reinforced, injection molding

General Information				
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.12	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Vertical flow direction: 270°C, 2.00mm ¹	0.90	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.30	--	%	ISO 2577
Flow direction: 270°C, 2.00mm ³	1.0	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.30	--	%	ISO 2577
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3200	1000	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	80.0	45.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	4.0	24	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	2800	1000	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	90.0	30.0	MPa	ISO 178/A
23°C ⁶	105	40.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	6.0	7.0	%	ISO 178/A
ISO Shortname	PA 6, GR, 14-030	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	< 10	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	30	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)				ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	20	kJ/m ²	ISO 180/1A

Unnotched Izod Impact Strength				ISO 180/1U
-30°C	200	--	kJ/m ²	ISO 180/1U
23°C	No Break	No Break		ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	25.0	--	J	ISO 6603-2
23°C	55.0	--	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	4400	--	N	ISO 6603-2
23°C	5000	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	172	--	°C	ISO 75-2/B
1.8 MPa, not annealed	66.0	--	°C	ISO 75-2/A
Melting Temperature ⁸	221	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	1.0E-4	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	8.0E-5	--	cm/cm/°C	ISO 11359-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	260 - 280		°C	
Mold Temperature	80.0 - 90.0		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

